

Details


Company Name:	Nisse Venho
Project Name:	Betonipäivät 2024
Section Name:	Seinä
Sensor Name:	Seinä
Tagged by:	Nisse Venho
Pouring Time:	2024-02-02 12:26:50
Concrete Mix:	Cobuilt
Ready Mix Producer:	-
Threshold:	Betonipäivät seinä (22 MPa)



Test results

	Cable	Body
Max. Temperature:	22.26 °C	22.3 °C
Min. Temperature:	18.08 °C	18.23 °C
Maturity Index:	4425.76 °C-hrs	4451.42 °C-hrs
Strength:	24.24 MPa	24.31 MPa

Temperature & Strength



Maturity

